

การสึกของสารซีแลนท์จากการแปร่งด้วยแปร่งสีฟันชนิดต่าง ๆ

: การศึกษาในห้องปฏิบัติการ

สลิลลา ตรีกาลนนท์* ทบ., ป.บัณฑิต (ทันตกรรมทั่วไป)

แพรวพัชร ปัจฉิมสวัสดิ์** ทบ., Cert. in Pediatric Dentistry, M.S.

วนิดา นิมนานนท์** ทบ., ป.บัณฑิต (ปริทัศน์วิทยา)

*คลินิกทันตกรรม 33 บ้านรักฟัน 48/30 วงศ์กรพลาซ่า ถนนสายไหม กรุงเทพฯ 10220

**ภาควิชาทันตกรรมโรงพยาบาล คณะทันตแพทยศาสตร์ มหาวิทยาลัยมหิดล 6 ถนนโยธี เขตราชเทวี กรุงเทพฯ 10400

บทคัดย่อ

วัตถุประสงค์ของการศึกษานี้เพื่อประเมินการสึกของสารซีแลนท์เมื่อแปร่งด้วยแปร่งสีฟันเด็กและแปร่งสีฟันผู้ใหญ่ โดยศึกษาความชรุระผิวและความลึกของการสึกเป็นดัชนีบ่งชี้ นำชิ้นตัวอย่างของสารซีแลนท์มาแปร่งโดยใช้เครื่องแปร่งฟันไฟฟ้า ร่วมกับสารละลายยาสีฟันเป็นจำนวน 6,000 12,000 24,000 36,000 และ 48,000 ครั้ง ในการศึกษาความชรุระผิว และ 48,000 ครั้ง ในการศึกษาความลึกของการสึก โดยใช้ชิ้นตัวอย่างจำนวน 12 ชิ้นต่อชนแปร่งหนึ่งชนิด นำค่าเฉลี่ยการสึก (ผลต่างความชรุระผิวก่อนและหลังแปร่ง) และความลึกของการสึกในแต่ละกลุ่มมาเปรียบเทียบทางสถิติ ผลการศึกษาพบว่ากลุ่ม แปร่งสีฟันเด็ก การสึกของสารซีแลนท์ไม่แตกต่างกันไม่ว่าจะใช้ชนิดชนแปร่งอ่อนหรืออ่อนมาก ($p > .05$) ยกเว้นที่ 12,000 ครั้งของการแปร่ง ($p < .05$) ส่วนความลึกของการสึกของชนแปร่งทั้งสองชนิดแตกต่างกัน ($p < .05$) สำหรับกลุ่ม แปร่งสีฟันผู้ใหญ่ พบว่า การสึกส่วนใหญ่และความลึกของการสึกที่เกิดจากการแปร่งด้วยชนแปร่งชนิดแข็งและปานกลางไม่ต่างกัน ($p > .05$) เช่นเดียวกับการแปร่งด้วยชนแปร่งชนิดอ่อนและอ่อนมาก แต่เมื่อเปรียบเทียบระหว่างการแปร่งด้วยชนแปร่งชนิดแข็งและปานกลางกับชนแปร่งชนิดอ่อนและอ่อนมาก พบว่าการสึกและความลึกของการสึก มีความแตกต่างกัน ($p < .05$) จากการศึกษาพบว่า การสึกของสารซีแลนท์จากการแปร่งด้วยชนแปร่งชนิดต่าง ๆ ดังกล่าวข้างต้น มีค่าน้อยมาก คือ น้อยกว่า 0.3 ไมโครเมตร

รหัสคำ: การสึก, สารซีแลนท์, แปร่งสีฟัน

สลิลลา ตรีกาลนนท์, แพรวพัชร ปัจฉิมสวัสดิ์, วนิดา นิมนานนท์. การสึกของสารซีแลนท์จากการแปร่งด้วยแปร่งสีฟันชนิดต่าง ๆ : การศึกษาในห้องปฏิบัติการ ว ทนต มหิดล 2549; 26: 207-17.



Sealant wear after brushing with various types of toothbrushes : An *in vitro* study

Salila Trikalnon* D.D.S., Grad. Dip. in Clin. Sc. (General Dentistry)

Praewpat Pachimsawat** D.D.S., Cert. in Pediatric Dentistry, M.S.

Vanida Nimmanon** D.D.S., Grad. Dip. in Clin. Sc. (Periodontics)

*33 Dental Home 48/30 Wongsakorn Plaza, Saimai Road, Bangkok 10220 Thailand.

**Department of Hospital Dentistry, Faculty of Dentistry, Mahidol University, 6 Yothi Street, Rachathewi, Bangkok 10400 Thailand.

Abstract

The objective of this study was to evaluate the sealant wear resulted from brushing with children or adult toothbrushes by using surface roughness and depth of wear as indices. Twelve sealant samples in each type of toothbrushes were abraded using a toothbrushing machine and slurry of toothpaste at 6,000, 12,000, 24,000, 36,000 and 48,000 brushing strokes in surface roughness study and only at 48,000 strokes in depth of wear study. Means of sealant wear (surface roughness differences between before and after brushing) and depth of wear were statistically compared. The results showed that soft and supersoft bristles of *children toothbrushes* had no difference when sealant wear was compared ($p > .05$) except at 12,000 brushing strokes ($p < .05$). In contrast, differences were found in depth of wear ($p < .05$). In *adult toothbrushes*, no significant difference in most of sealant wear and depth of wear was observed when compared between brushing with hard and medium bristles as well as soft and supersoft bristles. However, sealant wear and depth of wear resulted from brushing with hard and medium bristles were significant differences in comparison with soft and supersoft bristle ($p < .05$). This study found that brushing with all types of toothbrushes causes much less sealant wear which were less than $0.3 \mu\text{m}$.

Key words: wear, sealant, toothbrush

Trikalnon S, Pachimsawat P, Nimmanon V. Sealant wear after brushing with various types of toothbrushes : An *in vitro* study.
Mahidol Dent J 2006; 26: 207-17.